



DECLARATION OF PERFORMANCE

No 0160/019

Rev. 02

Product Identification Code	Hot rolled steel product for Structural Use. Grade S355K2W as for EN10025-5:2005	
Identification	According to the information stated on the ID label with barcode and/or Bundle number and in the Inspectin certificate.	
Intended use of the Construction Product	Flat product for use in metal structures or in metal complexes and concrete structures.	
Manufacturer (registered office)	Marcegaglia S.p.A. Via Bresciani, 16 – 46040 Gazoldo degli Ippoliti (MN) – Italia	
Production Plant	San Giorgio di Nogaro Via Fermi, n°33 - 33058 San Giorgio Nogaro (UD) - Italia	
System of assessment and verification of the continuity of performance of the construction product	2+	
Name and ID number of the notified Body	RINA Service S.p.A. – Via Corsica, 12 – 16128 Genova - Italia 0474	
Certificates of Conformity for the control of the plant production have been issued for the following elements: <ul style="list-style-type: none"> Starting inspection of the production plant and of the factory production control. Surveillance, evaluation and regular audits of the factory production control. 		
DECLARED PERFORMANCE		
Main Features	Performance	Harmonised specification
Dimensional tolerances	As for (EN 10029: 2011)Table 2	EN 10025-5: 2005
Elongation	As for Table 1	
Tensile strength		
Yield strength		
Impact strength		
Chemical analysis	As for Table 3	
Durability (with no request for coating)	N.P.D.	
The performance of the above mentioned product complies with the set of declared performances. This responsibility statement is issued in accordance with Regulation (EU) No. 305/2011, under the sole responsibility of the manufacturer identified above.		
Signed for and behalf of Marcegaglia S.p.A.		
<i>Marco Ing. Ferrone</i> San Giorgio di Nogaro Plant Manager		<i>San Giorgio di Nogaro 29/01/2015</i>
This declaration of performance is valid only in presence of the product identification label and delivery document or of the inspection certificate.		



TABLE 1 – MECHANICAL CHARACTERISTICS

grade	<i>Minimum Yield strenght Reh^{a)} Mpa</i>						<i>Tensile strenght Rm^{a)} Mpa</i>	
	Nominal Thickness (mm)							
	≤ 16	> 16 ≤ 40	> 40 ≤ 63	> 63 ≤ 80	> 80 ≤ 100	> 100 ≤ 120	≥ 3 ≤ 100	> 100 ≤ 120
S355	355	345	335	325	315	295	470 to 630	450 to 600
a) For plate, strip and wide flats with widths. ≥600 mm the direction transverse (t) to the rolling direction applies. For all other products the values apply for the direction parallel (l) to the rolling direction..								

TABLE 1 – MECHANICAL CHARACTERISTICS (follows)

grade	Position of test pieces ^{a)}	<i>Mechanical characteristics at room temperature for steel grades with impact strenght values</i>				<i>Impact strenght KV longitudinal for flat products</i>	
		Min. percentage elongation after break ^{a)} % L0=5,65√S0				temperature °C	Minimum energy (J)
		Nominal Thickness (mm)					
		≥ 3 ≤ 40	> 40 ≤ 63	> 63 ≤ 100	> 100 ≤ 120	≤ 120	
S355	l	22	21	20	18	-20	40
	t	20	19	18	18		
a) For plate, strip and wide flats with widths. ≥600 mm the direction transverse (t) to the rolling direction applies. For all other products the values apply for the direction parallel (l) to the rolling direction.							

TABLE 3 – CHEMICAL ANALYSIS

Chemical composition of the ladle analysis of steel with improbe atmospheric corrosion resistance^{d)}

grade	C % max	Si % max	Mn %	P % max	S % max	N % max	Aggiunta di elementi che fissano l'azoto ^{c)}	Cr %	Cu %
S355	0,16	0,50	0,50 - 1,50	0,030	0,030		yes-	0,40 - 0,80	0,25 - 0,55

- a) It is permissible to exceed the specified values provided that for each increase of 0.001% N the P max. content will be reduced by 0.005%; the N content of the ladle analysis, however, shall not be more than 0.012%
- b) The max. value for nitrogen does not apply if the chemical composition shows a minimum total Al content of 0.020 % or if sufficient other N binding elements are present..The binding elements shall be mentioned in the inspection document.
- c) The steels shall contain at least one of the following elements: Al total ≥ 0,020%, Nb: 0,015% - 0,060%, V: 0,02% - 0,12%, Ti: 0,02 - 0,10%.If these elements are used in combination, at least one of them shall be present with the minimum content indicated.
- d) The steels may show a Ni content of max.0.65%, 0.30% Mo, 0.15% Zr.



TABLE 2 – DIMENSIONAL TOLERANCES

Tolerance on thickness (mm)

Dimensions (mm)	class A		class B		class C		class D	
	min	max	min	max	min	max	min	max
Nominal thickness t								
$8 \leq t < 15$	-0,5	+0,9	-0,3	+1,1	0	+1,4	-0,7	+0,7
$15 \leq t < 25$	-0,6	+1,0	-0,3	+1,3	0	+1,6	-0,8	+0,8
$25 \leq t < 40$	-0,7	+1,3	-0,3	+1,7	0	+2	-1,0	+1,0
$40 \leq t < 80$	-0,9	+1,7	-0,3	+2,3	0	+2,6	-1,3	+1,3
$80 \leq t < 150$	-1,1	+2,1	-0,3	+2,9	0	+3,2	-1,6	+1,6

Tolerances on width for plates with trimmed edges a)

Dimensions (mm)	Tolerance on width for trimmed edges	
Nominal thickness t	Lower	Upper
$t < 40$	0	+20
$40 \leq t < 150$	0	+25

a) Tolerances on width for plates with untrimmed edges shall be the subject of agreement between the manufacturer and purchaser at the time of enquiry and order

Tolerances on length

Dimensions (mm)	Tolerances on length	
Nominal length t	Lower	Upper
$l < 4000$	0	+20
$4000 \leq l < 6000$	0	+30
$6000 \leq l < 8000$	0	+40
$8000 \leq l < 10000$	0	+50
$10000 \leq l < 15000$	0	+75
$15000 \leq l \leq 20000$	0	+100

Tolerances on flatness

Dimensions (mm)	Normal tolerances (class N)		Special tolerances (class S)	
	Measuring length (mm)		Measuring length (mm)	
Nominal thickness t	1000	2000	1000	2000
$8 \leq t < 15$	7	11	3	6
$15 \leq t < 25$	7	10	3	6
$25 \leq t < 40$	6	9	3	6
$40 \leq t < 150$	5	8	3	6

For anything not specified in tables or for exceptions as established in the reference standards