

<b>DECLARATION OF PERFORMANCE</b>	
<b>NR C3014</b>	
<b>Rev. 4</b>	
Unique identification code of the product type	<b>S275JR</b>
Intended use/es	Konstrukcje metalowe lub konstrukcje złożone z metalu i betonu.
Manufacturer (registered office)	<b>Marcegaglia Poland Sp. z o.o.</b> ul. Kaliska 72, 46-320 Praszka
Production Plant	<b>Ligota Dolna</b> ul. Przemysłowa 1, 46-200 Kluczbork
System (-s) of assessment and verification of the constancy of performance	<b>2+</b>
Harmonized specification	<b>EN 10025-1:2004</b>
Notified Body (-s)	RINA Service S.p.A. – Via Corsica, 12 – 16128 Genova - Italia <b>0474</b>

Certificates of Conformity for the control of the plant production have been issued for the following elements:

- initial inspection of the production plant and of the factory production control.
- surveillance, evaluation and regular audits of the factory production control.

<b>DECLARED PERFORMANCE</b>		
Main Features	Performance	Harmonized Technical Specification
Dimensional Tolerances	EN10051:2010	EN10025-1:2004
Elongation	EN10025-2:2019	
Tensile strength		
Yield strength		
Impact strength		
Weldability (CEV)		
Durability	Possibility for hot-dip galvanizing by specifying option 5 at the ordering time	

The performance of the product identified above is in conformity with the set of declared performance/s. This declaration of performance is issued, in accordance with Regulation (EU) No 305/2011, under the sole responsibility of the manufacturer identified above.

**TABLE 1 - MECHANICAL CHARACTERISTICS**

Mechanical properties for steel grades quality groups with impact strength values specified

STEEL GRADE	ReH <sup>(a)</sup> MPa <sup>(b)</sup> Min	Rm <sup>(a)</sup> MPa <sup>(b)</sup>		Min. Percentage elongation after break % <sup>(a)</sup>								Impact strength KV <sup>(c)</sup>	
				Lo = 80 (mm)						Lo = 5,65√So	Temp. (°C)	Min energy (J)	
				Nominal Thickness (mm)									
				≤ 16	< 3	≥ 3 ≤ 100	<sup>(a)</sup>	≤ 1	> 1 ≤ 1,5	> 1,5 ≤ 2	> 2 ≤ 2,5	> 2,5 < 3	≥ 3 ≤ 40
S275JR	275	430 + 580	410 ÷ 560	l	15	16	17	18	19	23	20	27	
				t	13	14	15	16	17	21			

a) For sheets and strips ≥ 600 mm wide, these values relate to samples taken in a direction transverse (t) to the rolling direction. For all other products, the values for samples taken in parallel (l) to rolling direction are applied

b) MPa = 1N/mm<sup>2</sup>

Signed for and on behalf of Marcegaglia Poland Sp. z o.o.:

  
**Filippo Nicoli**  
 Marcegaglia Poland Sp. z o.o. Director

Ligota Dolna, 28.02.2020

This declaration of performance is valid only in presence of the product identification label and delivery document or of the inspection certificate issued at the delivery.